



# Multi-objective factors optimization in fused deposition modelling with particle swarm optimization and differential evolution

Mohamed Arezki Mellal<sup>1</sup> · Chahinaze Laifaoui<sup>1</sup> · Fahima Ghezal<sup>1</sup> · Edward J. Williams<sup>2,3</sup>

Received: 17 December 2021 / Accepted: 24 February 2022  
© The Author(s), under exclusive licence to Springer-Verlag France SAS, part of Springer Nature 2022

## Abstract

The design of any system contemplates the elaboration of a prototype of the entire system or some parts, before the manufacturing phase. Nowadays, rapid prototyping (RP) is widely used by the designers. Achieving good manufacturing performances needs to handle various process parameters. Most works deal with single objective process parameters. The reality is quite different and the processes involve conflicting objectives. This paper addresses the multi-objective factors optimization of the fused deposition modelling (FDM) technology. The problem is converted into a single one using the weighted-sum method and then solved by resorting to two nature-inspired computing techniques, namely particle swarm optimization (PSO) and differential evolution (DE). The results obtained are compared.

**Keywords** Rapid prototyping · Fused deposition modelling · Multi-objective optimization · Weighted-sum method · Particle swarm optimization · Differential evolution

## 1 Introduction

For many years, the industry has been continuously evolving due to the increasingly great demand from consumers, and machining processes are widely used, including conventional and nonconventional processes [1–5]. One of the most important things in the industry is the prototype, which is a miniature or a scaled model of a product to be created. In previous years, the prototype was manually made by molding and it took a long time to manufacture; then with the rapid development of technology, rapid prototyping (RP) can make complex 3D shapes that are made using a Computer Aided Design (CAD) with different processes, to reduce time, minimize cost and achieve complex shapes that cannot be manufactured by machining. Nowadays, various techniques are used, such as 3D

printing, or virtual and augmented reality [6, 7]. To obtain a high quality object, it is necessary to optimize the processes. The prototyping processes can be found in several fields, such as medicine, aerospace/aeronautics, and robotics.

Nowadays, the optimization of the prototyping processes remains a challenge for the researchers. Most of the optimization approaches used to solve engineering problems are nature-inspired due to their effectiveness [8]. This paper provides a nonexecutive review of the literature. Comprehensive reviews can found in Refs. [9–17]. Jandyal et al. [18] also provided a review published in 2022. Lee et al. [19] used the Taguchi method to optimize the fused deposition modeling (FDM) to produce the acrylonitrile butadiene styrene. The FDM has many parameters to be handled [20]. These parameters have an impact on the physical and mechanical properties of the designed products [21]. Naveed [22] stated that the raster angle is one of the most important parameters of the FDM. Udroi and Nedelcu [23] investigated the inkjet printing and polymer jetting using CATIA software, but the results were not compared to those achieved by alternate methods. Wang et al. [24] used the Taguchi method with the Gray relational analysis to optimize the FDM. The results were compared to the prediction. Sood et al. [25] proposed empirical models for the FDM to improve the tensile, flexural and impact strength responses by considering

✉ Mohamed Arezki Mellal  
mellal.mohamed@gmail.com

<sup>1</sup> LMSS, Faculty of Technology, M'Hamed Bougara University, Boumerdes, Algeria

<sup>2</sup> Industrial and Manufacturing Systems Engineering Department, College of Engineering and Computer Science, University of Michigan, Dearborn 48126, USA

<sup>3</sup> Decision Sciences, College of Business, University of Michigan, Dearborn 48126, USA

five process parameters: layer thickness, orientation, raster angle, raster width, and air gap. Variance analysis was used to test the model. Rao and Rai [16] used the teaching–learning-based optimization (TLBO) and the non-dominated sorting TLBO algorithm to solve single and multi-objective prototyping processes, including the model developed by Sood et al. [25]. The Pareto was generated to find the set of optimal solutions. However, selecting one single solution from the Pareto set led to conflicting conclusions. Shirmohammadi et al. [26] implemented the artificial neural network (ANN) with the particle swarm optimization (PSO) to minimize the surface roughness of a 3D printing process. They concluded that the proposed hybrid approach reduced the error. Addressing multi-objective process parameters is a key element to achieve good performances and remains a challenge. Only a few works have investigated the latter.

In this paper, the multi-objective FDM process is addressed and optimized with the weighted-sum method and the optimal parameters are provided using the PSO and the differential evolution (DE). The remainder of the paper is organized as follows: Sect. 2 describes the problem. Sections 3 and 4 give the description of the implemented PSO and DE, respectively. Section 5 provides the results with a discussion. Finally, the last section concludes the paper with remarks and suggested directions for future work.

## 2 Multi-objective FDM process

The FDM is a RP process that uses a moving nozzle to extrude a polymeric material fiber [25, 27–30]. Based on empirical models, the multi-objective optimization problem of the FDM is given as follows [16, 25]:

$$\begin{aligned} \text{Maximize } T_s \text{ [MPa]} \\ = 13.5625 + 0.7156A - 1.3123B + 0.9760C + 0.5183E \\ + 1.1671A^2 - 1.3014B^2 - 0.4363(A \times C) + 0.4364(A \times D) \\ - 0.4364(A \times E) + 0.4364(B \times C) + 0.4898(B \times E) \\ - 0.5389(C \times D) + 0.5389(C \times E) - 0.5389(D \times E) \quad (1) \end{aligned}$$

$$\begin{aligned} \text{Maximize } F_s \text{ [MPa]} \\ = 29.9178 + 0.8719A - 4.8741B + 2.4251C - 0.9096D \\ + 1.6626E - 1.7199(A \times C) + 1.7412(A \times D) - 1.1275(A \times E) \\ + 1.0621(B \times E) + 1.0621(C \times E) - 1.0408(D \times E) \quad (2) \end{aligned}$$

$$\begin{aligned} \text{Maximize } I_s \text{ [MJ/m}^2\text{]} \\ = 0.401992 + 0.034198A + 0.008356B + 0.013673C \\ + 0.02138A^2 + 0.008077(B \times D) \quad (3) \end{aligned}$$

Subject to the following design variables:

$$0.127 \text{ mm} \leq A \leq 0.254 \text{ mm} \quad (4)$$

$$0^\circ \leq B \leq 30^\circ \quad (5)$$

$$0^\circ \leq C \leq 60^\circ \quad (6)$$

$$0.4064 \text{ mm} \leq D \leq 0.5064 \text{ mm} \quad (7)$$

$$0 \text{ mm} \leq E \leq 0.008 \text{ mm} \quad (8)$$

where  $T_s$  [MPa] is the tensile strength,  $F_s$  [MPa] is the flexural strength,  $I_s$  [MJ/m<sup>2</sup>] is the impact strength,  $A$  [mm] is the layer thickness,  $B$  [degree] is the orientation,  $C$  [degree] is the raster angle,  $D$  [mm] is the raster width, and  $E$  [mm] is the air gap.

In this paper, the multi-objective problem described in Eqs. (1)–(3) is converted into a single objective problem using the weighted-sum method [31–34] as follows:

$$\text{Maximize } Z = w_1T_s + w_2F_s + w_3I_s \quad (9)$$

where  $Z$  is the one-scaled objective function and  $w_i$  ( $i = 1, 2, 3$ ;  $w_1 + w_2 + w_3 = 1$ ) are the weight factors for each objective function.

## 3 Particle swarm optimization

The particle swarm optimization (PSO) is a nature-inspired optimization algorithm inspired by the moving mechanism of swarms, such as flocks of birds and schools of fishes. It was initially developed by Kennedy and Eberhart [35]. It is based on the position and the velocity of the particles of the swarm. PSO is one of the strongest optimization algorithms which has proven its effectiveness to tackle various engineering problems, such as the design of system availability and cost [33, 36], trajectory planning of robots [37], the combined heat and power economic emission dispatch problem [38], and system reliability [34]. Details on the PSO can be found in Refs. [35, 39, 40]. The pseudo-code of the implemented PSO to solve the above problem is given in Algorithm 1.

**Algorithm 1.** Pseudo-code of the implemented PSO.

Input the parameters;

Generate random solutions;

**While** No. of iterations  $\leq$  max No. of iterations **Do**

Evaluate the one-scaled objective function and constraint handling using penalty functions;

Move the particles;

Update the position and the velocity;

Find best position and velocity;

**End while**

Display the results:  $Z$ ,  $Ts$ ,  $Fs$ ,  $Is$ ,  $A$ ,  $B$ ,  $C$ ,  $D$ , and  $E$ .

---

## 4 Differential evolution

The differential evolution (DE) is a nature-inspired optimization algorithm inspired by the population evolution mechanisms. It was developed by Storn and Price [41] and is based on the genetic algorithms [42] but is characterized by more perturbations during iterations. Many works used the DE due to its robustness, such as PID controller [43], maintenance planning [44], state of charge estimation of batteries [45], and system availability [46]. More details on the DE can be found in Refs. [41, 46–48]. The pseudo-code of the implemented DE to solve the above problem is given in Algorithm 2.

**Algorithm 2.** Pseudo-code of the implemented DE.

Input of the parameters;

Generate random solutions;

**While** No. of iterations  $\leq$  max No. of iterations **Do**

Evaluate the one-scaled objective function and constraint handling using penalty functions;

Perform evolution mechanisms;

Perturbations during iterations;

**End while**

Display the results:  $Z$ ,  $Ts$ ,  $Fs$ ,  $Is$ ,  $A$ ,  $B$ ,  $C$ ,  $D$ , and  $E$ .

---

## 5 Results and discussion

The problem described has been solved using the above two algorithms and implemented using MATLAB 2017 and run on a PC with the following characteristics: i5 of 2.50 GHz with 4 GB. Each algorithm has been run over ten independent runs. The population size is 20 and the maximum number of iterations is 100. These parameters have been fixed by trial-and-error and based on experience. The weight factors are considered equal, i.e. ( $w_1 = w_2 = w_3 = 0.3333$ ).

Tables 1 and 2 report the results obtained by the PSO and the DE over the ten runs, respectively. The values of the one-scaled objective ( $Z$ ), the three process performances ( $Ts$ ,  $Fs$  and  $Is$ ), design variables, number of function evaluations (NFE), CPU time, and standard deviation ( $\sigma$ ) are included.

---

**Table 1** Results obtained by the PSO

Run #	$T_s$ [MPa]	$F_s$ [MPa]	$I_s$ [MJ/m <sup>2</sup> ]	$Z$	$A$ [mm]	$B$ [°]	$C$ [°]	$D$ [mm]	$E$ [mm]	NFE	CPU [s]	$\sigma$
1	170.2548	125.3745	1.3162	<b>98.8849</b>	0.1270	7.6880	60	0.4064	0.008	1660	17.28	2.8E-04
2	170.4601	125.1358	1.3167	<b>98.8849</b>	0.1270	7.7105	59.9944	0.4064	0.008	1960	20.23	
3	170.5864	125.0318	1.3170	98.8845	0.127	7.7331	60	0.4064	0.007	1980	12.18	
4	170.3061	124.9912	1.3161	<b>98.8849</b>	0.127	7.7191	59.9466	0.4064	0.008	1840	11.90	
5	170.2408	125.3889	1.3162	<b>98.8849</b>	0.1270	7.6609	60	0.4064	0.008	<b>1220</b>	12.23	
6	170.2634	125.3570	1.3162	98.884	0.1270	7.6671	59.9989	0.4065	0.008	2000	12.38	
7	170.3064	125.3283	1.3163	98.8848	0.127	7.6741	60	0.4064	0.008	1720	11.57	
8	170.3662	125.1776	13.165	<b>98.8849</b>	0.1274	7.6934	59.9956	0.4065	0.008	2000	11.81	
9	170.4134	125.2184	1.3166	<b>98.8849</b>	0.127	7.6967	60	0.4064	0.008	1980	11.74	
10	170.3698	125.2216	1.3165	<b>98.8849</b>	0.127	7.6931	59.9936	0.4065	0.008	1680	11.95	

Bold values represent the best results

**Table 2** Results obtained by the DE

Run #	$T_s$ [MPa]	$F_s$ [MPa]	$I_s$ [MJ/m <sup>2</sup> ]	$Z$	$A$ [mm]	$B$ [°]	$C$ [°]	$D$ [mm]	$E$ [mm]	NFE	CPU[s]	$\sigma$
1	170.3954	125.2397	1.3166	<b>98.8849</b>	0.1270	7.6923	60	0.4064	0.008	600	15.37	0
2	170.3954	125.2397	1.3166	<b>98.8849</b>	0.1270	7.6923	60	0.4064	0.008	500	9.90	
3	170.3954	125.2397	1.3166	<b>98.8849</b>	0.1270	7.6923	60	0.4064	0.008	620	9.78	
4	170.3954	125.2397	1.3166	<b>98.8849</b>	0.1270	7.6923	60	0.4064	0.008	640	9.38	
5	170.3954	125.2397	1.3166	<b>98.8849</b>	0.1270	7.6923	60	0.4064	0.008	500	9.52	
6	170.3954	125.2397	1.3166	<b>98.8849</b>	0.1270	7.6923	60	0.4064	0.008	620	9.43	
7	170.3954	125.2398	1.3166	<b>98.8849</b>	0.1270	7.6923	60	0.4064	0.008	660	9.83	
8	170.3954	125.2397	1.3166	<b>98.8849</b>	0.1270	7.6923	60	0.4064	0.008	560	9.18	
9	170.3954	125.2397	1.3166	<b>98.8849</b>	0.1270	7.6923	60	0.4064	0.008	<b>440</b>	9.89	
10	170.3954	125.2398	1.3166	<b>98.8849</b>	0.1270	7.6923	60	0.4064	0.008	660	9.58	

Bold values represent the best results

**Table 3** Comparison of PSO vs DE

	$Z$	NFE	CPU[s]	$\sigma$
PSO	<b>98.8849</b>	1980	12.23	2.8E-04
DE	<b>98.8849</b>	<b>440</b>	<b>9.89</b>	<b>0</b>

Bold values represent the best results

From Table 1, it can be observed that the best value of  $Z$  obtained by the PSO is 98.8849 for all runs, except #3, #6 and #7. The fewer NFE corresponds to #5 (1,220) with 12.23 s of CPU time. The optimal values are  $T_s = 170.2408$  MPa,  $F_s = 125.3889$  MPa,  $I_s = 1.3162$  MJ/m<sup>2</sup>, whereas the decision variables are  $A = 0.1270$  mm,  $B = 7.6880^\circ$ ,  $C = 60^\circ$ ,  $D = 0.4064$  mm, and  $E = 0.008$  mm. The standard deviation of the ten runs is 2.8E-04.

From Table 2, it can be observed that the best value of  $Z$  obtained by the DE is 98.8849 for all runs. The lower NFE corresponds to #9 (440) with 9.89 s of CPU time. The optimal values are  $T_s = 170.3954$  MPa,  $F_s = 125.2397$  MPa,

$I_s = 1.3166$  MJ/m<sup>2</sup>, whereas the decision variables are  $A = 0.1270$  mm,  $B = 7.6923^\circ$ ,  $C = 60^\circ$ ,  $D = 0.4064$  mm, and  $E = 0.008$  mm. The standard deviation of the ten runs is 0.

Table 3 summarizes the best results obtained by the PSO and the DE. It can be observed that both algorithms obtained the same value of the one-scale objective ( $Z = 98.8849$ ). However, the performances of the DE have outperformed those of the PSO in terms of number of function evaluations, CPU time, and standard deviation.

## 6 Conclusions

The goal of this paper was to investigate the multi-objective fused deposition modelling (FDM) optimization problem which is a rapid prototyping process (RP). The considered objectives were the tensile strength, the flexural strength, and the impact strength. The multi-objective problem was converted to a single one using the weighted-sum method in order to avoid the disadvantages of the Pareto set. The particle swarm optimization (PSO) and differential evolution (DE) were implemented with constraint handling to solve the problem. It was shown that both algorithms provides the same value of the one-scaled objective, but the performances of the DE were better. The latter means that the DE required fewer function evaluations, required less CPU time, and has a lower standard deviation. Therefore, the present work contributes to the machinability of the FDM process by providing the optimal process parameters when considering both objectives, i.e., the tensile strength, the flexural strength, and the impact strength. Future work will be devoted to the development of a hybrid approach to improve the results and solve other rapid prototyping processes.

**Authors' contributions** Mohamed Arezki Mellal conceived of the study, designed the study, supervised the study, and wrote the manuscript. Chahinaze Laifaouia and Fahima Ghezal investigated the study, programmed the study, and collected the results. Edward J. Williams designed the study and revised the manuscript.

**Funding** This study has not received funds.

**Data availability** The data sets supporting the results of this article are included within the article.

## Declarations

**Conflict of interest** The authors declare no competing interests.

**Consent for publication** All authors agree to transfer copyright of this article to the Publisher.

## References

- Mellal, M.A., Williams, E.J.: Total production time minimization of a multi-pass milling process via cuckoo optimization algorithm. *Int. J. Adv. Manuf. Technol.* (2016). <https://doi.org/10.1007/s00170-016-8498-3>
- Mellal, M.A., Williams, E.J.: Parameter optimization of advanced machining processes using cuckoo optimization algorithm and hoopoe heuristic. *J. Intell. Manuf.* **27**, 927–942 (2016). <https://doi.org/10.1007/s10845-014-0925-4>
- Mellal, M.A., Laifaoui, C., Ghezal, F.: Multi-objective factors optimization in fused deposition modelling with particle swarm optimization and differential evolution. 10 August 2021, PREPRINT (Version 1) available at Research Square (2021). <https://doi.org/10.21203/rs.3.rs-777037/v1>
- Daniyan, I.A., Balogun, V., Mpfu, K., Omigbodun, F.T.: An interactive approach towards the development of an additive manufacturing technology for railcar manufacturing. *Int. J. Interact. Des. Manuf.* **14**, 651–666 (2020). <https://doi.org/10.1007/S12008-020-00659-8/FIGURES/18>
- Galati, M., Minetola, P.: On the measure of the aesthetic quality of 3D printed plastic parts. *Int. J. Interact. Des. Manuf.* **14**, 381–392 (2020). <https://doi.org/10.1007/S12008-019-00627-X/TABLES/5>
- Meng, L., Zhang, W., Quan, D., Shi, G., Tang, L., Hou, Y., Breitzkopf, P., Zhu, J., Gao, T.: From topology optimization design to additive manufacturing: today's success and tomorrow's roadmap. *Arch. Comput. Methods Eng.* **27**, 805–830 (2020). <https://doi.org/10.1007/S11831-019-09331-1>
- Wang, Q., Tan, Y., Mei, Z.: Computational methods of acquisition and processing of 3D point cloud data for construction applications. *Arch. Comput. Methods Eng.* **2019**(27), 479–499 (2019). <https://doi.org/10.1007/S11831-019-09320-4>
- Mellal, M.A., Adjerid, S., Williams, E.J., Benazzouz, D.: Optimal replacement policy for obsolete components using cuckoo optimization algorithm based-approach: dependability context. *J. Sci. Ind. Res.* **71**, 715–721 (2012)
- Peltola, S.M., Melchels, F.P.W., Grijpma, D.W., Kellomäki, M.: A review of rapid prototyping techniques for tissue engineering purposes. *Ann. Med.* **40**, 268–280 (2008). <https://doi.org/10.1080/07853890701881788>
- Mohamed, O.A., Masood, S.H., Bhowmik, J.L.: Optimization of fused deposition modeling process parameters: a review of current research and future prospects. *Adv. Manuf.* **3**, 42–53 (2015). <https://doi.org/10.1007/s40436-014-0097-7>
- Kakde, N.U., Deshbhratar, V.J.: Rapid prototyping: A review. *Int. J. Eng. Res. Gen. Sci.* **4**, 114–119 (2016)
- Coon, C., Pretzel, B., Lomax, T., Strlič, M.: Preserving rapid prototypes: a review. *Heritage Sci* **4**(1), 1–16 (2016)
- Wiberg, A., Persson, J., Olvander, J.: Design for additive manufacturing—a review of available design methods and software (2019)
- Plocher, J., Panesar, A.: Review on design and structural optimisation in additive manufacturing: towards next-generation lightweight structures. *Mater. Des.* **183**, 108164 (2019). <https://doi.org/10.1016/j.matdes.2019.108164>
- Zhu, J., Zhou, H., Wang, C., Zhou, L., Yuan, S., Zhang, W.: A review of topology optimization for additive manufacturing: Status and challenges. *Chin. J. Aeronaut.* (2021). <https://doi.org/10.1016/j.cja.2020.09.020>
- Rao, R.V., Rai, D.P.: Optimization of fused deposition modeling process using teaching-learning-based optimization algorithm. *Eng. Sci. Technol. Int. J.* (2016). <https://doi.org/10.1016/j.jestch.2015.09.008>
- Madheswaran, S., Sivakumar, K., Prakash, E., Kalaivanan, S., Someswaran, N., Vishnudeepan, J.: Applications of additive manufacturing—a review. In: *Advances in Materials Research*, pp. 21–27. Springer, Singapore (2021)
- Jandyal, A., Chaturvedi, I., Wazir, I., Raina, A., Ul Haq, M.I.: 3D printing—a review of processes, materials and applications in industry 4.0. *Sustain. Oper. Comput.* **3**, 33–42 (2022). <https://doi.org/10.1016/J.SUSOC.2021.09.004>
- Lee, B.H., Abdullah, J., Khan, Z.A.: Optimization of rapid prototyping parameters for production of flexible ABS object. *J. Mater. Process. Technol.* (2005). <https://doi.org/10.1016/j.jmatprotec.2005.02.259>
- Naveed, N.: Investigating the material properties and microstructural changes of fused filament fabricated PLA and tough-PLA parts. *Polym.* **13**, 1487 (2021). <https://doi.org/10.3390/POLYM13091487>
- Chadha, A., Ul Haq, M.I., Raina, A., Singh, R.R., Penumarti, N.B., Bishnoi, M.S.: Effect of fused deposition modelling process parameters on mechanical properties of 3D printed parts. *World J. Eng.*



- 16, 550–559 (2019). <https://doi.org/10.1108/WJE-09-2018-0329/FULL/XML>
22. Naveed, N.: Investigate the effects of process parameters on material properties and microstructural changes of 3D-printed specimens using fused deposition modelling (FDM). *Mater. Technol.* **36**, 317–330 (2021). <https://doi.org/10.1080/10667857.2020.1758475>
  23. Udriou, R., Nedelcu, A.: Optimization of additive manufacturing processes focused on 3D printing. In: *Rapid Prototyping Technology—Principles and Functional Requirements*, pp. 1–28. InTech (2011)
  24. Wang, C.C., Lin, T.W., Hu, S.S.: Optimizing the rapid prototyping process by integrating the Taguchi method with the Gray relational analysis. *Rapid Prototyp. J.* **13**, 304–315 (2007). <https://doi.org/10.1108/13552540710824814>
  25. Sood, A.K., Ohdar, R.K., Mahapatra, S.S.: Parametric appraisal of mechanical property of fused deposition modelling processed parts. *Mater. Des.* (2010). <https://doi.org/10.1016/j.matdes.2009.06.016>
  26. Shirmohammadi, M., Goushchi, S.J., Keshtiban, P.M.: Optimization of 3D printing process parameters to minimize surface roughness with hybrid artificial neural network model and particle swarm algorithm. *Prog. Addit. Manuf.* (2021). <https://doi.org/10.1007/s40964-021-00166-6>
  27. Altıntaş, E., Özkan, B., Yener, G.: Porous scaffolds. In: *Nanobiomaterials Science, Development and Evaluation*, pp. 27–59. Elsevier (2017)
  28. Zein, I., Huttmacher, D.W., Tan, K.C., Teoh, S.H.: Fused deposition modeling of novel scaffold architectures for tissue engineering applications. *Biomaterials* **23**, 1169–1185 (2002). [https://doi.org/10.1016/S0142-9612\(01\)00232-0](https://doi.org/10.1016/S0142-9612(01)00232-0)
  29. Sachlos, E., Czernuszka, J.T.: Making tissue engineering scaffolds work Review on the application of solid freeform fabrication technology to the production of tissue engineering scaffolds. *Eur Cells Mater* **5**, 29–40 (2003). <https://doi.org/10.22203/ecm.v005a03>
  30. Chim, H., Huttmacher, D.W., Chou, A.M., Oliveira, A.L., Reis, R.L., Lim, T.C., Schantz, J.T.: A comparative analysis of scaffold material modifications for load-bearing applications in bone tissue engineering. *Int. J. Oral Maxillofac. Surg.* **35**, 928–934 (2006). <https://doi.org/10.1016/j.ijom.2006.03.024>
  31. Zadeh, L.A.: Optimality and non-scalar-valued performance criteria. *IEEE Trans. Autom. Control* **8**, 59–60 (1963). <https://doi.org/10.1109/TAC.1963.1105511>
  32. Mellal, M.A., Salhi, A., Williams, E.J.: Accelerated cuckoo optimization algorithm for the multi-objective welding process. *J. Braz. Soc. Mech. Sci. Eng.* **42**, 6 (2020). <https://doi.org/10.1007/s40430-019-2089-9>
  33. Mellal, M.A., Salhi, A.: Parallel–Series System Optimization by Weighting Sum Methods and Nature-Inspired Computing. *Applied Nature-Inspired Computing: Algorithms and Case Studies*. Springer, Singapore pp. 231–251 (2020). [https://doi.org/10.1007/978-981-13-9263-4\\_10](https://doi.org/10.1007/978-981-13-9263-4_10)
  34. Mellal, M.A., Zio, E.: An adaptive particle swarm optimization method for multi-objective system reliability optimization. In: *Proceedings of the Institution of Mechanical Engineers, Part O: Journal of Risk and Reliability*. 1748006X1985281 (2019). <https://doi.org/10.1177/1748006X19852814>
  35. Kennedy, J., Eberhart, R.: Particle swarm optimization. *Neural Networks*, 1995. In: *Proceedings. IEEE International Conference*, Vol. 4, pp. 1942–1948 (1995). <https://doi.org/10.1109/ICNN.1995.488968>
  36. Mellal, M.A., Zio, E.: Multi-objective availability and cost optimization by PSO and COA for series-parallel systems with subsystems failure dependencies. *Microprocess. Microsyst.* **89**, 104422 (2022). <https://doi.org/10.1016/j.micpro.2021.104422>
  37. Fernandes, P.B., Oliveira, R.C.L., Fonseca-Neto, J.V.: Trajectory planning of autonomous mobile robots applying a particle swarm optimization algorithm with peaks of diversity. *Appl. Soft Comput.* **116**, 108 (2022). <https://doi.org/10.1016/J.ASOC.2021.108108>
  38. Xiong, G., Shuai, M., Hu, X.: Combined heat and power economic emission dispatch using improved bare-bone multi-objective particle swarm optimization. *Energy* **244**, 123108 (2022). <https://doi.org/10.1016/J.ENERGY.2022.123108>
  39. Mellal, M.A., Williams, E.J.: A Survey on Ant Colony Optimization, Particle Swarm Optimization, and Cuckoo Algorithms, pp. 37–51 (2018). <https://doi.org/10.4018/978-1-5225-2990-3.ch002>
  40. Hamadache, I., Mellal, M.A.: Design optimization of car side safety system by particle swarm optimization and grey wolf optimizer. In: Mellal, M.A., Pecht, G.M. (eds.) *Nature-inspired computing paradigms in systems: reliability, availability, maintainability, safety and cost (RAMS+C) and prognostics and health management (PHM)*. Elsevier (2021). <https://doi.org/10.1016/B978-0-12-823749-6.00006-4>
  41. Storn, R., Price, K.: *Differential evolution—a simple and efficient adaptive scheme for global optimization over continuous spaces*. Berkeley, CA, USA (1995)
  42. Holland, J.H.: *Adaptation in Natural and Artificial Systems* (1975)
  43. AbouOmar, M.S., Su, Y., Zhang, H., Shi, B., Wan, L.: Observer-based interval type-2 fuzzy PID controller for PEMFC air feeding system using novel hybrid neural network algorithm-differential evolution optimizer. *Alex. Eng. J.* (2022). <https://doi.org/10.1016/J.AEJ.2021.12.072>
  44. Abdelkader, E.M., Moselhi, O., Marzouk, M., Zayed, T.: An exponential chaotic differential evolution algorithm for optimizing bridge maintenance plans. *Autom. Constr.* **134**, 104107 (2022). <https://doi.org/10.1016/J.AUTCON.2021.104107>
  45. Wang, C., Xu, M., Zhang, Q., Feng, J., Jiang, R., Wei, Y., Liu, Y.: Parameters identification of Thevenin model for lithium-ion batteries using self-adaptive Particle Swarm Optimization Differential Evolution algorithm to estimate state of charge. *J. Energy Storage.* **44**, 103244 (2021). <https://doi.org/10.1016/J.EST.2021.103244>
  46. Mellal, M.A., Zio, E.: Availability optimization of parallel-series system by evolutionary computation. In: *3rd International Conference on System Reliability and Safety*. Barcelona, Spain (2018). <https://doi.org/10.1109/ICSRS.2018.8688722>
  47. Zio, E., Golea, L.R., Sansavini, G.: Optimizing protections against cascades in network systems: a modified binary differential evolution algorithm. *Reliab. Eng. Syst. Saf.* **103**, 72–83 (2012). <https://doi.org/10.1016/j.res.2012.03.007>
  48. Zio, E., Viadana, G.: Optimization of the inspection intervals of a safety system in a nuclear power plant by Multi-Objective Differential Evolution (MODE). *Reliab. Eng. Syst. Saf.* **96**, 1552–1563 (2011). <https://doi.org/10.1016/j.res.2011.06.010>

**Publisher's Note** Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.